



westcoat®

Slip Resistance ASTM C-1028

System/ Sealer	Dry Static- Rubber Sole	Dry Sliding- Rubber Sole	Wet Static- Rubber Sole	Wet Sliding- Rubber Sole
ALX Standard/ SC-10	0.79	0.76	0.67	0.64
ALX Custom/ SC-70	0.68	0.65	0.62	0.56
MACoat Standard / SC-10	0.89	0.82	0.56	0.49
Dubro / EC-32	0.87	0.77	0.78	0.71
Thin Film / EC-95	0.51	0.50	0.44	0.33
Liquid Granite / EC-32	0.68	0.60	0.51	0.43
Liquid Terrazzo / EC-32	0.50	0.48	0.36	0.30
Liquid Dazzle / EC-96	0.57	0.55	0.48	0.45
Epoxy Mortar / EC-34	0.63	0.61	0.49	0.46
Texture Crete Knock Down / SC-10	0.79	0.76	0.67	0.64
Texture Crete Skip Trowel/ SC-70 w/Safe Grip	1.12	0.92	1.00	0.88
Texture Crete Custom / SC-70	0.68	0.65	0.62	0.56
Smoothfloor/ EC-95	0.65	0.61	0.60	0.50
Broom- on / SC-42	0.90	0.83	0.84	0.76
TC-0 / EC-100	0.50	0.47	0.48	0.41
Water-Based Stain / SC-42	0.73	0.70	0.68	0.65

* All systems met specifications with the stated Seal Coat, results will vary based on application methods & coverages. For accurate results it is recommended to test mock ups of individual application.

** Highlighted column is the Static Coefficient of Friction, the standard measure for skid resistance. The Occupational Safety and Health Administration recommends that walking surfaces have a static coefficient of friction of 0.5. A static coefficient of friction of 0.6 is recommended for accessible routes and 0.8 for ramps.