



WESTCOAT SYSTEM			ANSI A326.3/A137.1 BOT-3000E		ASTM C-1028
SYSTEM	CEMENT/TEXTURE	TOPCOAT	WET READING	DRY READING	DRY STATIC RUBBER SOLE
ALX Standard	TC-3 Knockdown	SC-10	0.32	0.64	0.81
ALX Standard	TC-3 Knockdown	SC-10 + CA-30	0.51	0.61	0.63
ALX Standard	TC-3 Knockdown	SC-10 + CA-31	0.52	0.64	0.86
ALX Custom Finish	TC-2 Skip Trowel	SC-70	0.54	0.65	0.71
ALX Custom Finish	TC-2 Skip Trowel	SC-70+CA-30	0.61	0.72	0.93
ALX Custom Finish	TC-2 Skip Trowel	SC-70+CA-31	0.56	0.69	0.94
ALX Solar Reflective Finish	TC-2 Smooth	SC-10 SR	0.61	0.72	0.86
MACoat Standard	WP-90 + TC-1 Slurry	SC-10	0.57	0.65	0.83
MACoat Standard	TC-3 Knockdown	SC-10	0.32	0.64	0.81
MACoat Standard	TC-3 Knockdown	SC-10 + CA-30	0.51	0.61	0.63
MACoat Standard	TC-3 Knockdown	SC-10 + CA-31	0.52	0.64	0.86
MACoat Custom Finish	TC-2 Skip Trowel	SC-70	0.54	0.65	0.71
MACoat Custom Finish	TC-2 Skip Trowel	SC-70+CA-30	0.61	0.72	0.93
MACoat Custom Finish	TC-2 Skip Trowel	SC-70+CA-31	0.56	0.69	0.94
MACoat Solar Reflective Finish	TC-2 Smooth	SC-10 SR	0.61	0.72	0.86
Dubro	30/60 Silica Sand Blend	EC-34	0.73	0.74	1.05
Dubro Quartz	TC-65 Quartz Sand	EC-32	0.71	0.8	0.92
Epoxy Mortar	TC-73	EC-34	0.44	0.44	0.31
Epoxy Mortar Quartz	TC-65	EC-32	0.42	0.44	0.31
Epoxy Pebbles	Aquarium	EC-84	0.52	0.61	0.51
Liquid Dazzle	N/A	EC-38	0.46	0.81	0.86
Liquid Dazzle	N/A	SC-65	0.34	0.55	0.66
Liquid Granite	TC-60 Chips	EC-102	0.37	0.56	0.71
Liquid Terrazzo	TC-60 Chips	EC-102	0.37	0.56	0.71
Temper-Crete	N/A	EC-24/TC-24	0.71	0.65	0.59
Temper-Crete Broadcast	30 Silica Sand Broadcast	EC-102	0.69	0.75	0.74
Thin Film 100% Solids	N/A	EC-34	0.44	0.44	0.31
Thin Film 100% Solids	N/A	EC-34 + CA-30	0.55	0.71	0.82
Thin Film 100% Solids	N/A	EC-34 + CA-31	0.56	0.69	0.96
Thin Film 100% Solids	N/A	EC-95 + CA-33 #60	0.79	-	-
Thin Film 100% Solids	N/A	EC-34 + CA-29	0.36	0.53	0.46
Thin Film Water-Based	N/A	EC-11	0.36	0.67	0.89
11-10 System	N/A	SC-10	0.38	0.64	0.79
11-10 Custom System	N/A	SC-65SG	0.35	0.55	0.66
Fast Stain Grind & Seal	Diamond Ground Concrete	EC-11	0.38	0.67	0.89
Fast Stain Polish	Polished Concrete	SC-24	0.48	0.59	0.59
Stamp-It	TC-6	SC-70	0.52	0.61	0.8
Texture-Crete Broom On	TC-5	SC-42	0.69	0.68	0.89
Texture-Crete Interior	TC-2	EC-32 + EC-95F	0.27	0.49	0.26
Texture-Crete Standard	TC-3 Knockdown	SC-10	0.32	0.64	0.81
Texture-Crete Standard	TC-3 Knockdown	SC-10 + CA-30	0.51	0.61	0.63
Texture-Crete Standard	TC-3 Knockdown	SC-10 + CA-31	0.52	0.64	0.86
Texture-Crete Custom Finish	TC-2 Skip Trowel	SC-70	0.54	0.65	0.71
Texture-Crete Custom Finish	TC-2 Skip Trowel	SC-70+CA-30	0.61	0.72	0.93
Texture-Crete Custom Finish	TC-2 Skip Trowel	SC-70+CA-31	0.56	0.69	0.94
Texture-Crete Solar Reflective Finish	TC-2 Smooth	SC-10 SR	0.61	0.72	0.86

For increased slip-resistance, Westcoat offers a wide variety of slip resistance additives that can be added to most topcoats and sealers. Data is based on in-house testing and is just for general reference as actual slip resistance values will greatly vary based on application methods, coverage rates, substrate conditions, etc. For accurate results, it is recommended to apply an on site mock-up and have slip resistance readings performed by a third-party, certified testing agency.