



**SC-30 Acid Stain**

**Description**

Westcoat SC-30 Acid Stain is made from an acid solution, wetting agents, and metallic ions. When this solution is placed on concrete it can color the concrete (or cement) by chemically combining the metallic ions with particles in the concrete to form oxides.

- Unique Colors
- Flat Finish
- Penetrating
- Permanent
- No Film Build Up
- Chemical Stain

**Uses**

SC-30 is designed to penetrate and react with concrete, and Westcoat cement, producing a variety of mottled colors. It can be used on both interior and exterior projects including showrooms, restaurants, cafes, breweries, garage, pool decks, patios and driveways.

**Packaging**

SC-30 (1 and 5 gallon pails)

**Color**

Aqua	Autumn Leaf	Avocado
Black	Blonde	Bronze
Canyon	Chestnut	Chocolate
Mint	Walnut	

**Advantages**

- Fast Drying

**INSPECTION / PREPARATION**

**Inspection**

Concrete must be clean, dry, and free of grease, paint, oil, dust, curing agents, or any foreign material that will prevent proper adhesion. The concrete should be at least 2500 psi and feel like 60 to 80 grit sandpaper. The concrete should be porous and be able to absorb water. A minimum of 28 days cured is required on all concrete. Prior to starting work, test existing concrete slab for efflorescence, moisture, and hydrostatic pressure.

**Preparation**

Prepare surface by sanding, power washing and/or power scrubbing to achieve a clean, uniform surface that will allow product to soak in and react with the cement in the concrete. Acid washing is not recommended and will be detrimental to the final effect. Clean surface entirely with TSP and/or a degreaser and rinse completely several times with clean water.

**APPLICATION**

**Thinning**

Thin SC-30 with up to 5 parts of water for staining concrete, and up to 20 parts of water when applying over Westcoat cements. Always do a sample before beginning the job. Thinning will effect the depth of color..

and desired color.

**Coverage**

The coverage will vary depending on the surface. Apply as thin as possible at 200-400 square feet per gallon on most surfaces, depending on strength.

Whether brushing or brooming, do so consistently, as it will effect how the acid reacts. As you brush the acid, it will foam and react with the concrete. Varying degrees of foaming will occur and some colors may not show right away, apply fresh acid ahead of the brush. The foamed material should not be applied to an untreated area, as it will not chemically stain the surface properly. Additional applications may be done to darken the surface further after the first application has dried. (You may also work 2 to 3 colors into the surface to achieve a unique look).

**Applying Product**

Using an acid resistant garden sprayer, spray the SC-30 Acid Stain onto the surface evenly. Immediately after spraying brush or broom the material into the concrete in a circular fashion. The surface may be predampened to increase the movement of the acid.

Once the surface has reacted and dried (usually 2-6 hours) you must scrub and rinse off all residue completely. This could be considered the most difficult part of the application. You can take advantage of this time to confirm the color, as the water will simulate the "wet look" of most sealers. Additional stain may be applied at this point, but you need to rinse again. Make sure to scrub, mop and completely rinse the surface 2-3 times, and wet vacuum until dry. Be sure to safely and properly dispose of the residue.

SC-30 can be thinned with up to 5 parts of water for staining concrete. Always do a sample before beginning the job. Thinning will effect the depth of color. The coverage will vary depending on the surface. Apply as thin as possible at 200-400 square feet per gallon on most surfaces, depending on strength, porosity of the concrete

Failure to completely remove all residues prior to sealing the surface will cause appearance defects, adhesion loss or peeling, reduced durability, and possible bonding failure and delaminating of the sealer.

#### Clean Up

Uncured material can be removed with soap and water. If cured, material can only be removed mechanically.

---

### LIMITATIONS

- This product is designed for professional use only.
- Do not apply at temperatures below 50°F or above 90°F.
- Be sure to paper off any areas that you do not want stained.
- Will not hide imperfections or stains in concrete.
- Product will stain concrete and can produce a mottled look. Colors and effects will vary.
- Acid Stain will fade with prolonged exposure to sunlight.
- Older concrete may not accept stain.
- Do not allow Westcoat product to freeze.

---

### HEALTH PRECAUTIONS

Inhalation of vapor or mist can cause headache, nausea, irritation of nose, throat, and lungs. Prolonged or repeated skin contact can cause slight skin irritation.

#### Caution

This product contains hydrochloric acid. Wear goggles and rubber gloves when handling. Mask out all surrounding surfaces, and be sure that area is well ventilated. Store unused material in plastic containers only. Metal containers must not be used.

---

### DISCLAIMER

PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT

OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.



4007 Lockridge Street San Diego, CA 92102  
800•250•4519 • Fax 619•255.7187 • westcoat.com

SC-30 9/16