



TC

TEXTURE COAT
DECORATIVE TEXTURED SURFACES

TC-0 Micro Cement

Description

TC-0 Micro Cement is a special formulated portland cement blended with a variety of fine silica sands and proprietary additives.

Uses

TC-0 is primarily used in conjunction with WP-81 Cement Modifier, and in many of Westcoat Systems when a very smooth surface is required. Primly used in interior applications for an ultra smooth surface.

Advantages

- High Strength
- Good Working time
- Cement Products Can be Feathered
- Excellent Adhesion to Most Surfaces
- Increases Water Resistance
- Safe Water-Based- No Solvents
- Can be Sanded
- Use For a Smooth Floor
- Reduced "Burn Marks"

Packaging

45 lb bags and 56 bags per pallet.

INSPECTION / PREPARATION

Inspection

Concrete must have ¼ inch slope per linear foot with at least 2500 psi with a rough broom finish (like 60 to 80 grit sand paper) and be open and porous. Allow concrete a minimum 28 days to cure. Test existing concrete slab for efflorescence moisture and hydrostatic pressure.

Preparation

On concrete remove all coatings to a sound concrete base. Prepare surface by grinding, water blasting or shot blasting to achieve surface that feels like 60 to 80 grit sand paper.

APPLICATION

Mixing

Add 1 gallon of WP-81 and up to 3/4 gallon of water, using a mechanical mixer mix thoroughly.

trowel multiple thin layers to achieve a super smooth surface.

Coverage

1000 square feet to 2000 square feet per bag. Coverage will vary depending on use.

Dry Time

1 to 4 hours depending on use and climate.

Applying Product

May be troweled, squeegeed, or broomed. For best results

Clean Up

Uncured material can be removed with soap and warm water. If cured, material can only be removed mechanically or with an environmentally safe solvent.

LIMITATIONS

- This system is designed for professional use only.
- Read System Specification Sheets before beginning the project.
- Do not apply at temperatures below 50°F or above 90°F.
- Best applied over TC-2, TC-4 or TC-5
- Surface will be smooth and likely slippery avoid using outside.

- Rain will wash away uncured Westcoat acrylic products.
- If inclement weather threatens, cover area to protect new application.
- Store material between 40°F-90°F.
- Do not allow Westcoat product to FREEZE.
- Use dustless equipment when possible.

HEALTH PRECAUTIONS

Inhalation of vapor or mist can cause headache, nausea, irritation of nose, throat and lungs. Prolonged or repeated skin contact can cause slight skin irritation.

Contains portland cement. Wear rubber gloves and eye protection. Avoid eye contact and prolonged contact with skin. Wash thoroughly after handling. If eye contact occurs, flush with water for 15 minutes. Call a physician immediately.

DISCLAIMER

PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT

OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.



westcoat®

4007 Lockridge Street San Diego, CA 92102
800•250•4519 • Fax 619•255.7187 • westcoat.com