



KEYNOTES

- ① Concrete Substrate
- ② Wall
- ③ CA-53 Cove Cap (plastic)
- ④ FRP Edge Trim Molding
- ⑤ FRP
- ⑥ Epoxy Radius Cove
- ⑦ Epoxy Flooring System
- ⑧ Urethane Joint Sealant (By Others)

- Concrete must be a minimum 2,500 PSI.
- Concrete must be cured for a minimum 28 days.
- Concrete should be prepared to a profile equal to ICRI CSP 3-5.
- Refer to local building codes and standards.
- Refer to all Product and System Specifications for additional information.
- Epoxy Radius may vary depending on building code or facility requirements.
- Zinc Cove Cap can be used in lieu of CA-53.

REV. 4/20/23 - TC

EPOXY COVE - FRP PANEL TERMINATION WITH JOINT SEALANT

DIVISION 09 67 23
Resinous Flooring

SCALE : NTS



westcoat
SPECIALTY COATING SYSTEMS

4007 Lockridge Street • San Diego, CA • 92102
800.250.4519 • westcoat.com