



## KEYNOTES

- ① Concrete Substrate
- ② Temper-Crete Coat (EC-24 & TC-24)
- ③ Broadcast Aggregate (TC-65 or #30 silica sand)
- ④ Topcoat (EC-102)

- Optional Primer Coat can be installed as needed.
- Concrete must be a minimum 3,500 PSI.
- Concrete must be cured for a minimum 14 days.
- Concrete should be prepared to a profile equal to ICRI CSP 3-5.
- Refer to local building codes and standards.
- Refer to all Product and System Specifications for additional information.

REV. 6-2-22 TC

### TEMPER-CRETE SLB - SYSTEM OVERVIEW

DIVISION 09 67 23  
Fluid-Applied Flooring

SCALE : NTS



**westcoat**  
SPECIALTY COATING SYSTEMS

4007 Lockridge Street • San Diego, CA • 92102  
800.250.4519 • westcoat.com