

Acid Stain Training

Welcome to Westcoat's Self-Educated Training. The purpose of this course is to increase your knowledge of the Acid Stain system.

This is a two-step process that will take approximately 45 minutes to complete. You will be required to complete a short test and submit your answers.

Education

- 1. Training Video: This 5 minute video takes you through the step-by-step process of correctly installing **Acid Stain**.
- 2. Spec Sheet: These spec sheets contain detailed information on uses, materials and coverage rates for this system. The specs also have detailed instructions on the proper application steps from preparation to final coat to achieve a successful installation. Click below to read the spec sheets:

Acid Stain Grind and Seal

Acid Stain Prep and Seal

3. Materials Cost: Westcoat's Materials Cost Template is a powerful tool for you and your customers. Click below, find and download the Material Cost Template, then estimate the materials and associated cost a 500 sq ft job.

Acid Stain System Page > scroll down to find the Material Cost Template

*Alternatively, the **Material Estimator** shows the material needed without pricing.

4. Color Chart: The Acid Stain system is available in a variety of colors and finishes, click to review the color charts:

Acid Stain

5. Tools: Get familiar with the recommended tools needed to install this system.

Acid Stain Tool Guide

Now to test all the valuable knowledge you've learned, continue to the next page.

TEST

1. Is Acid Stain for both interior and exterior use?

Yes

No

2. Acid Stain reacts with concrete to produce unique colors.

True

False

3. Acid Stain has two versions, what are they?

Grind & Seal and Prep & Seal

Standard and Custom

4. Grind and Seal requires what type of concrete preparation?

Diamond grinding with 60-80 grit tools, sweep and vacuum.

Power wash and let dry.

5. Prep and Seal requires what type of concrete preparation?

Sweep and vacuum.

Prepare concrete to a profile equal to CSP 3, power wash and power scrub.

6. What tool is used to spray the acid stain?

A spray bottle

An acid resistant garden sprayer

7. The material should be brushed in long linear lines immediately after spraying.

True, lines will keep it uniform.

False, brushing in a circular motion will create movement.

8. How much can the SC-30 be thinned?

SC-30 can be thinned with up to 5 parts of water.

Do not thin this product ever.

9. What should be done after the the surface has reacted and dried?

Scrub and rinse off all residue completely.

Seal it immediately.

10. The recommended sealer for Grind and Seal is SC-65, what's the coverage rate?

600-800 square feet per gallon

200-400 square feet per gallon

Name:

Branch name/Location: