



Texture-Crete® Interior Training

Welcome to Westcoat's Self-Educated Training. The purpose of this course is to increase your knowledge of the Texture-Crete® Interior system.

This is a two-step process that will take approximately 45 minutes to complete. You will be required to complete a short test and submit your answers.

Education

1. Training Video: This 8 minute video takes you through the step-by-step process of correctly installing **Texture-Crete® Interior**.
2. Spec Sheet: These spec sheets contain detailed information on uses, materials and coverage rates for this system. The specs also have detailed instructions on the proper application steps from preparation to final coat to achieve a successful installation. Click below to read the spec sheet:

Texture-Crete® Interior

3. Materials Cost: Westcoat's Materials Cost Template is a powerful tool for you and your customers. Click below, find and download the Material Cost Template, then estimate the materials and associated cost a 500 sq ft job.

Texture-Crete® Interior Page > scroll down to find the **Material Cost Template**

*Alternatively, the **Material Estimator** shows the material needed without pricing.

4. Color Chart: The Texture-Crete® Interior system is available in a variety of colors and finishes, click to review the color charts:

Acid Stain

Liquid Colorant

Water-Based Stains

5. Tools: Get familiar with the recommended tools needed to install this system.

Texture-Crete Interior Tool Guide

Now to test all the valuable knowledge you've learned, continue to the next page.

TEST

1. What should the concrete be free of to ensure proper adhesion?
Grease, paint, oil, dust, curing agents, laitance or any foreign material.
Cracks and joints.
2. What should be done if you are unable to coat over the primer in the same day?
Broadcast #30 or #60 silica sand into the wet primer
It has to be coated over the same day.
3. What components make up the slurry coat?
WP-82 Cement Modifier / TC-2 Smooth or TC-4 Fine Cement / TC-40 Liquid Colorant
WP-81 Cement Modifier / TC-1 or TC-3 Cement / SC-10 Acrylic Topcoat
4. What should the coverage rate be of the slurry coat?
100 to 200 square feet per batch
200 to 250 square feet per batch
5. What components make up the texture coat?
WP-82 Cement Modifier / TC-2 Smooth or TC-4 Fine Cement / TC-40 Liquid Colorant
WP-81 Cement Modifier / TC-1 or TC-3 Cement / SC-10 Acrylic Topcoat
6. What should the coverage rate be of the texture coat?
100 to 200 square feet per batch
250 to 350 square feet per batch
7. What type of sprayers can be used to apply the Water-Based Stain?
A spray bottle
Pump sprayer, airless sprayer or HVLP sprayer
8. What can affect the Water-Based Stain coverage rate?
Texture and desired color.
The temperature.
9. What is the mixing ratio of the sealer?
Mix 2 parts A with 1 part B.
Mix 2 parts B with 1 part A.
10. How long until heavy objects can be placed on the surface?
12 hours
48 hours

Name:

Branch name/Location: