



Description

Westcoat SC-65SG WB Pigmented Polyurethane Sealer is a two component, high solids, water-based, pigmented, semi-gloss polyurethane sealer. SC-65SG provides properties equal to that of traditional urethanes (such as, ease of cleanability, gloss retention and excellent abrasion resistance) with fewer health and environmental concerns. The UV, mar and chemical resistant nature of this product allows it to outperform most other types of sealers.

Uses

SC-65SG Pigmented is designed to be used as the finish coat for numerous Westcoat systems, such as: Texture-Crete[®], Thin Film 100% Solids and Epoxy Slurry and can be applied over concrete, epoxies and cementitious coatings. SC-65SG works well in moderate chemical environments or in medium to heavy traffic areas. Water-based polyurethanes are low odor and non-flammable, making them ideal for interior applications. SC-65SG is appropriate for a variety of environments, such as: hospitals, schools, shopping centers, hotels, restaurants, clean rooms, pool decks and shop floors.

Advantages

Water-based • Low Odor • VOC Compliant • UV Resistant • Impact and Abrasion Resistant • Easy to Clean • Enhances Color • Non-yellowing • Good Working Time • Improved Dry Time • Excellent Adhesion • USDA & FDA Compliant • LEED Credit Points Available

Product Data			
Packaging	1 gal kit & 20 gal kit	Color	Black, Cape Cod Gray, Concrete Gray, Deep Tan, Pewter Gray, Safety Blue, Safety Green, Safety Red, Safety Yellow, Stone Gray, Travatan, Tile Red, White
Coverages	200-650 ft ² per gallon	Mix Ratio	3:1 (by volume)
VOC Content	<50 gm/l	Shelf Life	1 year in unopened packaging
Certifications VOC Emission Test Certificate: Berkeley Analytical - Certificate No: 180531-02			

Inspection

Surfaces must be structurally sound and it is recommended that they be sloped to help provide proper drainage. The surface must be dry and free of oil, grease, curing agents, dirt, dust or other foreign material that may prevent proper adhesion. The surface must be porous or rough enough to allow the product to soak in.

DISCLAIMER: PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.



westcoat[®]
SPECIALTY COATING SYSTEMS

**PRODUCT
SPECIFICATION**

SC

SURFACE COAT
PROTECTIVE SEALERS & STAINS

SC-65SG WB Pigmented Polyurethane Sealer

Moisture

All concrete should be tested for moisture before applying a seamless coating. If moisture emissions exceed 5 lbs/1000 square feet (ASTM F1869) or if the relative humidity (RH) exceeds 75% (ASTM F2170), contact the manufacturer before application.

Preparation

Concrete must be clean, dry and free of grease, paint, oil, curing agents, laitance or any foreign material that will prevent proper adhesion. Concrete should be prepared to a minimum surface profile of CSP 2, per ICRI. As a sealer over the ALX™, MACoat™ or Texture-Crete® Systems, apply directly over the textured surface. If texture has been left for more than 24 hours or it has become dirty, clean as needed prior to the application of SC-65SG.

As a final coat over textured epoxy systems, SC-65SG must be applied within 24 hours. If more than 24 hours have passed, lightly abrade the surface and wipe with a solvent, such as denatured alcohol, prior to the application.

Note: The most common reason for coating failure is due to lack of preparation.

Mixing

Premix each component separately. In a clean bucket, mix 3 parts A with 1 part B, by volume, of SC-65SG. Mix thoroughly with a low speed (200-300 rpm) drill motor for 2-3 minutes. Make sure to scrape the sides and bottom of the container during mixing. For best results, avoid mixing by hand.

Primer

For applications directly over concrete, it is recommended to prime the concrete with EC-12 Epoxy Primer, before applying SC-65SG Pigmented. SC-65SG must be applied within 24 hours after applying the EC-12. If more than 24 hours have passed, lightly abrade the surface and wipe with a solvent, such as denatured alcohol, prior to the application.

Thinning

Thinning is only recommended for use as a primer over cementitious coatings, such as Texture-Crete® Standard. Thin SC-65SG up to 10% for the first coat. It is not recommended to thin the final coat, as it may affect the hide or opacity. Thinning is not recommended over smooth and non-porous substrates. Thinning may affect the gloss, sheen and overall appearance of the product.

Coverage

Coverage for the SC-65SG is approximately 200 to 650 square feet per gallon.

Smooth Surfaces (such as Thin Film 100% Solids): coverage is approximately 400-650 square feet per gallon.

Textured Surfaces (such as Texture-Crete® or diamond ground concrete): coverage is approximately 200-400 square feet per gallon.

Coverage will vary based on the application methods, substrate conditions and overall desired finish.

DISCLAIMER: PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.



westcoat[®]

4007 Lockridge St • San Diego, CA 92102
800-250-4519 • Fax 619-255-7187 • westcoat.com

2 of 4
SC-65SG Pigmented 3/23



westcoat[®]
SPECIALTY COATING SYSTEMS

**PRODUCT
SPECIFICATION**

SC

SURFACE COAT
PROTECTIVE SEALERS & STAINS

SC-65SG WB Pigmented Polyurethane Sealer

Applying Product

The SC-65SG material may be rolled or sprayed with an airless sprayer. For best results, it is recommended to apply SC-65SG neat, with an airless sprayer over smooth or textured surfaces.

Smooth Surfaces: Immediately after mixing, apply SC-65SG onto the substrate. Apply with a squeegee and back roll with a ¼ to ¾ inch, high-quality, non-shedding roller cover, being sure to maintain a wet edge. Alternatively, SC-65SG can be dipped and rolled, if desired.

Textured Surfaces: SC-65SG can be sprayed with an airless sprayer. Alternatively, SC-65SG can be dipped and rolled with a ¾ to ½ inch, high-quality, non-shedding roller cover, being sure to maintain a wet edge.

For best results, two thin even coats should be applied. Do not over roll or overwork the material. Material must be applied thin and do not allow the material to puddle.

Re-coating

If needed, re-coat within 24 hours of application to ensure adhesion. If a delay occurs, it is recommended that the surface be lightly sanded and wiped with a solvent, such as denatured alcohol, just before reapplication.

Dry Time

You may re-coat as soon as the surface is dry to the touch or in about 4-8 hours. Light foot traffic may be permitted in 12 hours, normal traffic in 24 hours and vehicle traffic in 72 hours. All times are based on average temperature of 70F degrees and 50% humidity.

Clean Up

Equipment should be cleaned with water immediately after use.

Limitations

- This product is designed for professional use only.
- Be sure to do adequate surface preparation.
- Do not apply in temperatures below 50°F or above 80°F. Hot or cold weather may effect dry times. Avoid application if surface temperature is above 80°F.
- Surface will become more slippery when sealed. Skid resistant additives are available.
- Do not apply over damp surfaces.
- SC-65SG must be cured for a minimum of 48 hours before coming in contact with water.
- Do not allow any Westcoat products to freeze.


DISCLAIMER: PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.



westcoat[®]

4007 Lockridge St • San Diego, CA 92102
800-250-4519 • Fax 619-255-7187 • westcoat.com

3 of 4
SC-65SG Pigmented 3/23



westcoat[®]
SPECIALTY COATING SYSTEMS

**PRODUCT
SPECIFICATION**

SC

SURFACE COAT
PROTECTIVE SEALERS & STAINS

SC-65SG WB Pigmented Polyurethane Sealer

Health Precautions

Inhalation of vapor or mist can cause headache, nausea, irritation of nose, throat and lungs. Prolonged or repeated skin contact can cause slight skin irritation. Avoid contact with skin and wear protective gloves and eye protection. Read Safety Data Sheets prior to using.

Technical Data

Physical Properties

Chemical Composition	Water-Based Polyurethane
Density (#/gal)	10.79
Specific Gravity	1.1
Gloss @60 Degrees	45-55*
Solids %/wt	66 (+/- 1.0)
Solids %/vol	65 (+/- 1.0)
Viscosity cPs	700
Viscosity KU	85-95
VOC gm/l	<50
Shelf Life	1 year
Flash Point	NA

* Gloss variation is dependent on dry film thickness and substrate type

Technical Data

Pot Life (Gel Time) 150gm @72°F	1-1.5 hr.
Mix Ratio	3:1
Tack Free over concrete (@ 6 mil) @72°F	4 hr.
Foot Traffic -1st coat- over concrete @72°F	8 hr.
Foot Traffic -sealed surface- @72°F	12-16 hr.
Full Cure (@ 6 mil)	72 hr.
Pencil Hardness	2H
Adhesion on Concrete (7 day cure) ASTM D3359	5
Sag & Leveling ASTM D4400	4
Reducer/Clean Up	Water

Chemical Resistance

Muriatic Acid (31.5% HCL)	5
Sulfuric Acid (50% H2SO4)	5
Sulfuric Acid (93% H2SO4)	1
Nitric Acid (10% HNO3)	5
Sodium Hydroxide (50% NaOH)	5
Isopropyl Alcohol (99%)	4
Bleach (sodium hypochlorite)	5
Vinegar (3-5% acetic acid)	5
Transmission Fluid	5
Gasoline	5
Brake Fluid	5
409 Surface Cleaner	5
Pine Sol Solution	5
Blood & Body Fluids	5
Iodine Solution	5
Mustard	5s
Ketchup	5
Red Wine	5
Acetone	5
Methyl Ethyl Ketone (MEK)	5
Xylene	5
Skydrol	5
Ethanol	5
Methanol	5

Key:
5 = Best (no effect)
4 = Softens (recovers)
3 = Softens (no recovery)
2 = Blistered (no recovery)
1 = Worst Destroyed
s = With Stain
* Contact time > 5hrs = 1

DISCLAIMER: PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.



4007 Lockridge St • San Diego, CA 92102
800-250-4519 • Fax 619-255-7187 • westcoat.com

4 of 4
SC-65SG Pigmented 3/23