

	westcoat® SPECIALTY COATING SYSTEMS	PRODUCT SPECIFICATION
TC	TEXTURE COAT <small>DECORATIVE TEXTURED SURFACES</small>	TC-73 Epoxy Mortar Sand

Description

Westcoat TC-73 Epoxy Mortar Sand is a sub-angular, trowel grade aggregate. It is specifically designed to be used with trowel grade, resinous industrial flooring.

Uses

TC-73 is used in the Epoxy Mortar System to provide durable and high build in showrooms, commercial kitchens, warehouses, service areas, chemical processing plants, food processing plants, pharmaceutical facilities and auto dealerships.

Advantages

High Strength • Durable • High Build • Sub-Angular • Cost Effective • Impact Resistant

Product Data			
Packaging	50 lb Bag	Color	Tan
Coverages	Refer to System Specification	Mix Ratio	1 ½ gallons of EC-32 to 100 pounds of TC-73
VOC Content	0 gm/l	Shelf Life	Indefinite in unopened packaging

Inspection

Please refer to the desired System Specification Sheet for further information regarding Inspection.

Preparation

Please refer to the desired System Specification Sheet for further information regarding Surface Preparation.

Mixing

Mix 1 ½ gallons of EC-32 Clear Epoxy Topcoat with 100 pounds of TC-73 Epoxy Mortar Sand.

Applying Product

Please refer to the desired System Specification Sheet for further information regarding Application.

Clean Up

Uncured material can be removed with soap and warm water. If cured, material can only be removed mechanically or with an environmentally-safe solvent.

DISCLAIMER: PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.

	westcoat® SPECIALTY COATING SYSTEMS	PRODUCT SPECIFICATION
TC	TEXTURE COAT <small>DECORATIVE TEXTURED SURFACES</small>	TC-73 Epoxy Mortar Sand

Dry Time

Please refer to the desired System Specification Sheet for further information regarding Dry Time.

Limitations

- This product is designed for professional use only.
- It is strongly recommended that a sample be approved by the customer before starting the application.
- Westcoat assumes no responsibility for color variations after placement of material.
- Read System Specification Sheets before beginning the project.
- Color will vary depending on application.
- Do not allow any Westcoat products to freeze.

Health Precautions

Inhalation of vapor or mist can cause headache, nausea irritation of nose, throat and lungs. Avoid breathing vapors. It is strongly recommended that respirators are worn. Prolonged or repeated skin contact can cause slight skin irritation. Dry Pigments have the potential of causing skin irritations or allergic reactions. Be careful not to get on skin, clothes or in eyes. Gloves are strongly recommended. If splashed in the eye, flush with warm water and contact a physician if blurring persists.

Technical Data

Sieve	Retains (G)	Percentage
16 (1.19 mm)	0	0.00%
18 (1 mm)	6	0.49%
20 (0.841 mm)	22	1.81%
30 (0.595 mm)	126	10.39%
40 (0.420 mm)	296	24.40%
60 (0.250 mm)	590	48.64%
80 (0.177 mm)	117	9.65%
Pan	56	4/62%
Total	1213	100.00%

* The data set forth in this Product Data Sheet represents typical properties of the product described. The information and the typical values are not specifications. Westcoat cannot be responsible for the end use of its product. Final suitability of the product is the responsibility of the user.

DISCLAIMER: PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.