



## KEYNOTES

- ① Concrete Substrate
- ② Temper-Crete Coat & Broadcast Coat
- ③ 2nd Broadcast Coat
- ④ Polyaspartic Topcoats
- ⑤ WB Flat Polyurethane Sealer

- Concrete must be a minimum 3,500 PSI.
- Concrete must be cured for a minimum 14 days.
- Concrete should be prepared to a profile equal to ICRI CSP 3-4.
- Refer to local building codes and standards.
- Refer to all Product and System Specifications for additional information.

REV. 2/16/23

TIDALSTONE FLOORING SYSTEM - HIGH BUILD - SYSTEM OVERVIEW

DIVISION 09 67 23  
Fluid-Applied Flooring

SCALE : NTS



**westcoat**  
SPECIALTY COATING SYSTEMS

4007 Lockridge Street • San Diego, CA • 92102  
800.250.4519 • westcoat.com